

Chip Seal RT-CS

Product Description And Use

RT-CS is a water-based acrylic emulsion used in a variety of decorative concrete applications. It is available in both clear and pigmented formulations, dries quickly and is high in solids for single component emulsion type materials. RT-CS forms hard coating films, resists blushing and provides excellent resistance to yellowing in exterior applications. Pigmented RT-CS is used as a color coat over polymer concrete and spray applied decking. Clear RT-CS was designed as a fast drying build coat in color chip flooring and as an economical sealer over polymer concrete in light duty applications. It is an excellent primer on polymer concrete when two component polyurethane or polyurea/polyaspartics are used as finish coats.

Chemical Composition

Small particle size acrylic emulsion

Colors

14 standard colors available, plus clear

Limitations

- ⑩ Do not use directly over conventional concrete
- ⑩ Not recommended as a finish coat in high traffic areas or vehicle areas
- ⑩ When used as a clear over exterior polymer concrete, water can migrate through cracks and joints in the substrate and temporarily darken the host surface. This darkening disappears when the substrate dries.

Technical Data

Physical Properties

Solids Content, by Weight (Clear)	35%
Solids Content, by Weight (Pigmented)	47%
Gloss, 60°F (Clear)	82
Volatile Organic Compounds	75 gms./ltr.

Dry Times (77°F)

Re-Coat	30-60 minutes
Light Traffic	4-6 hours
Full Cure	72 hours

Higher temperatures, lower humidity, and good ventilation will shorten dry times.
Lower temperatures, high humidity, and poor ventilation will lengthen dry times.

Chip Seal RT-CS

WARRANTY INFORMATION

ResinTek Systems guarantees that this product is free from manufacturing defects and complies with our published specifications. In the event that the buyer proves that the goods received do not conform to these specifications or were defectively manufactured, the buyer's remedies shall be limited to either the return of the goods and repayment of the purchase price or replacement of the defective material at the option of the seller. ResinTek Systems MAKES NO OTHER WARRANTY, EXPRESSED OR IMPLIED, AND ALL WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE HEREBY DISCLAIMED. ResinTek Systems shall not be liable for damages caused by application of its products over concrete with excessive moisture vapor transmission or alkalinity. ResinTek Systems shall not be liable for any injury incurred in a slip and fall accident. Manufacturer or seller shall not be liable for prospective profits or consequential damages resulting from the use of this product.

Chemical and Stain Resistance (ASTM D-1308 24 Hour Exposure)

Mustard.....	no effect
Coffee.....	no effect
Cola.....	no effect Grape
Juice.....	no effect
Urine.....	no effect
Whiskey.....	no effect Motor
Oil.....	no effect
Gasoline.....	film softens Brake
Fluid.....	film destroyed Lacquer
Thinner.....	film destroyed

General Information

Surface Preparation

Surface must be free of all grease, oil and soils that may interfere with adhesion. Polymer concrete must be cleaned using a pressure washer (minimum psi 2,500) or detergent scrubbed with a floor machine using a nylogrit brush. Use RTS Orange Clean 8 parts water to 1 part detergent. Rinse well to remove all detergent residue.

Chip Seal RT-CS

Surface Preparation

Surface must be free of all grease, oil and soils that may interfere with adhesion. Polymer concrete must be cleaned using a pressure washer (minimum psi 2,500) or detergent scrubbed with a floor machine using a nylogrit brush. Use RTS Orange Clean 8 parts water to 1 part detergent. Rinse well to remove all detergent residue.

Application Recommendations

Surface to be coated may be damp, but with no visible water. RT-CS is best applied using the dip and roll method working out of a 5 gallon pail. Use a ½ or ¾ inch nap roller cover depending upon the texture of the surface. Use a cross-hatch rolling technique to insure an even distribution. Coverage will vary between 200-350 sq. ft. per gallon depending upon the substrate. More film thickness always adds to the quality of the job – do not stretch the material.

Re-Coat Information

RT-CS may be re-coated with itself or water-based polyurethanes as soon as the material can be walked on. Allow an overnight dry before re-coating with solvent-borne top coats. RT-CS may be re-coated without additional preparation for an indefinite period. However, if several days has elapsed and the surface has become dirty, re-cleaning is necessary.

Handling Precautions

Avoid contact with skin; wear protective gloves. Read Material Safety Data Sheet before using.

Slip and fall Precautions

OSHA and the American Disabilities Act (ADA) have now set enforceable standards for slip resistance on pedestrian surfaces. The current coefficient of friction required by ADA is .6 on level surfaces and .8 on ramps. ResinTek Systems recommends the use of angular slip resistant aggregate in all coatings or flooring systems that may be exposed to wet, oily or greasy conditions. It is the contractor and end users' responsibility to provide a flooring system that meets current safety standards. ResinTek Systems or its sales agents will not be responsible for injury incurred in a slip and fall accident.